

SUPER SEAL BROOM SWEPT CONCRETE CRACK FILLER

With White Sand to match the texture, color, and overall appearance of

BROOM SWEPT CONCRETE

Bottle: 1 Quart (946 ml) Net Weight 4 lbs (1.8 kg) Settling will occur.

NOTE: Liquid bonding agent will dry clear. Crack filler will dry to concrete's natural earth tone. Layer Crack Filler at depths of no more than a 1/4" at a time. Temperature must be above 50 Fahrenheit. In cool weather separation can occur. For best results, seal broom swept concrete with SUPER SEAL-M

DIRECTIONS:

1. Clean concrete well. Power washer will restore appearance.
2. Allow concrete to dry.
3. **SHAKE WELL!** Continue to shake well throughout application. Once opened, secure top while shaking. Shake upside down.
4. Snip spout on cap to desired width of pour.
5. Pour crack filler into crack. Tamp excess into crack, if necessary.
6. For large cracks, sweep with broom in direction of existing broom swept concrete.
7. Allow filler to dry before sealing. In warmer temperatures it will dry faster than in cooler temperatures.
8. Seal with SUPER SEAL B-COAT tm to protect and beautify concrete.

DISCLAIMER: Manufacturer warrants the product to be free from defects and will replace or refund the purchase price of said products proven defective. Since the manufacturer has no control over handling, use, or storage; no guarantee express or implied is offered. The suitability of the product for any use shall be solely up to the user. Manufacturer retains right to legal venue.

PATENT PENDING

Made in USA

CLEMONS CONCRETE COATINGS

**505 CAVE ROAD ★ NASHVILLE, TN 37210 ★ (615) 872-9099 ★ WWW.CCC-
USA.COM**