

SUPER SEAL - B

Water-Based CONCRETE SEALER

- Available in 15% solids (B-15) stock, 25% (B-Coat) stock, & 30% (B-30) special order
- CURING COMPOUND per ASTM C 309 (B-15)
- CURING COMPOUND per ASTM C 309 & C 1315 (B-COAT & B-30)
- TOP COATS & PROTECTS
- SEALS WATER OUT & BEADS WATER
- CLEAR SATIN SHEEN KEEPS CONCRETE NEW LOOKING
- NON-YELLOWING PROTECTION FROM SUN
- DUST-PROOFS
- WATER BASED, NON-FLAMMABLE, & ENVIRONMENTALLY FRIENDLY
- EASY TO APPLY & CLEANS UP WITH WATER

SURFACE PREPARATION

NEW CONCRETE: Apply as soon as bleed water has evaporated and concrete now longer has a wet sheen and can be walked upon. Spray evenly with a pump up sprayer.

EXISTING CONCRETE: Surface must clean & dry. Scrub oil spots with concrete cleaner. We recommend Old South Cleaner. Pressure-wash with water. Allow at least 24 hours to dry. Surface must be free of other coatings, waxes, and paint. Always test a small area to your satisfaction before proceeding.

APPLICATION: Apply at substrate temperatures above 50° F. Use a long nap roller or airless pump sprayer. Thoroughly saturate surface. Apply at approximately 200 ft² per gallon on brushed concrete and 300 ft² per gallon on smooth-troweled concrete. That may vary due to roughness and porosity of surface.

DRYING TIME: Allow three hours for foot traffic and 72 hours for automobile traffic. Do not apply if rain is imminent.

CLEAN UP: Wash with water.

NOTE: Keep from freezing. Store above 40° F.

CAUTION: Use with adequate ventilation. Avoid direct contact. Symptoms of exposure are redness and irritation to skin and burning and blurred vision to eyes.

FIRST AID:

- * EYES-Flush thoroughly for 15 minutes. Seek medical attention.
- * SKIN-Wash with soap & water. If irritation persists, seek medical attention.
- * INTERNAL- Do not induce vomiting. Call a doctor or poison control immediately.
- * INHALATION-Move to fresh air. Consult doctor if breathing difficulty persists.
- * SKIN ABSORPTION-No harmful results expected.

COMPONENTS:

Water
Ammonia salt of modified styrene acrylic polymers
Dipropylene glycol n-butyl ether

CAS#

7732-18-5
Proprietary
29911-28-2

Made in USA

Clemons Concrete Coatings ★505 Cave Rd. Nashville, TN 37210 ★ www.ccc-usa.com